

THE PLATINUM PACKAGING GROUP


Film Application And Temps

Lidding Film Temp Stats

PlatPeel Lidding to PP and
HDPE Cups 320 to 370 F
No Dot

PlatSeal Non
Peel Lidding To PP Only
320 to 390 F

PlatSeal EVA
Peeling Lidding To
OPS / PET / ALL CPETS 260 – 300 F



*TEMPERATURES ARE ESTIMATIONS FROM MANUFACTURERS OF THE FILM, ACTUAL OPERATING TEMPERATURES MAY VARY DEPENDING ON SPEED OF MACHINE, OPERATING ENVIRONMENT AND AGE & CONDITION OF MACHINE