

FILM PRODUCT	SEALING TO								GAUGE	FEATURES OF FILM
	PP	APET	RPET	CPET	ALU /FOIL	PS	PE	PVC		
SPX (AF) SPX 30 SPX LT 30 SPX 55 * **	NS	***	***	**	**	NS	NS	***	50,75 100, 120	# Strong peel film for APET & APET lined CPET trays. Ideal for produce packing & general use
HSPET9 HPP * **	NS	Weld	Weld	NS	NS	NS	NS	**	60, 80, 120	\$ # Weld seal for lidding and overwrap Ideal for HPP High Pressure Pasteurization
Plat GPG / GPE * **	**	***	***	***	***	***	***	***	50, 75, 100	# Seals all substrates. Ideal for mono-CPET
Plat GPG 8 * **	**	**	**	**	**	**	**	**	50, 75, 100	# Seals all substrates. Ideal for mono-CPET / Stronger than GPG for sealing
Seal2Foil (AF) *	NS	NS	NS	NS	***	NS	NS	NS	208	\$ # Laminate sealing to foil trays. Sterilisable. Can be high barrier
Plat Peel EVA * ** Available in H Barrier too	***	**	***	***	***	***	***	***	208	Laminates sealing to all substrates. Good for misaligned sealing moulds.
Plat Peel HT * ** Available in H barrier too	***	NS	NS	NS	NS	NS	***	NS	170, 200	\$ Retortable, boilable peelable laminate for PP & HDPE trays. Barrier
Plat Non Peel **	Weld	NS	NS	NS	NS	NS	NS	NS	188	Non Peel to PP Cont.
*Plat Non Peel HPP**	Weld	Weld	Weld	NS	NS	NS	Weld	Weld	168	Non Peel HPP
PlatSeal Non Peel PE Available in H barrier too	NS	NS	NS	NS	NS	NS	NS	NS	168	Non Peel to PE
Plat CAW **HSPET 6 CA Pizza Film * **	NS	*	*	NS	NS	NS	NS	*	50, 100	# Peelable PET when HSPET H. All other pizza overwrap
HSPET 6 **	NS	*	*	NS	NS	NS	NS	NS	50, 100	“ “ “ “
HSPET 9**	NS	Weld	Weld	NS	NS	NS	NS	Weld	60,80,120	# Mainly for overwrapping / Ovenable. Non Peel to PET
Resealer	Weld	Weld	Weld	Weld	Weld	Weld	Weld	Weld	200	Different grades available to seal to PP, PS, APET & PE

** Stocked Item * Microwaveable and freeze able # Ovenable \$ Hot Sterilisable + ETO sterilisable

***STRONG PEEL ** MEDIUM PEEL *EASY PEEL NS: NO SEAL