


## EVA (E) HC 200

### LAMINATION FILMS



#### STANDARD THICKNESS - 2.1 MIL

EVA (E) HC 200 is a medium barrier, peelable lidding film. This lidding film gives excellent seal-peel performance on APET, CPET, PVC, PP and PS containers.

#### Key Features

- Medium oxygen and moisture barrier
- Suitable for microwave heating
- Suitable for food contact
- Great as lidding material for fresh or frozen foods
- Max sealing temperature: 338 - 347°F

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
<b>MECHANICAL</b>			
Tensile Strength MD TD	lb/in <sup>2</sup>	ASTM D882	9,300 8,900
Elongation MD TD	%	ASTM D882	100 100
<b>PHYSICAL</b>			
Yield	in <sup>2</sup> /lb		12,600
COF Sealant side Heat resistant side		ASTM D1894	<.40 0.5
Haze	%	ASTM D1003	4-6
<b>BARRIER</b>			
MVTR	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 100%RH	0.5
OTR	cc/100 in <sup>2</sup> /day	ASTM D3985 23°C, 0%RH	6
<b>THERMAL</b>			
Recommended Sealing Temperature	F		284-320°

#### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

#### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

*Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Platinum Packaging Group assumes no liability whatsoever in connection with the use of this information.*