

## HT (E) 180

### LIDDING FILMS



#### STANDARD THICKNESS - 1.8 MIL

HT (E) 180 is a high clarity, medium barrier, peelable lidding film. This medium peel lidding film is designed to adhere to multiple substrates.

#### Key Features

- Medium moisture and oxygen barrier
- Strong, durable film
- Superior machinability
- Great as lidding material for fresh or frozen foods
- Max sealing temperature: 338 - 347°F

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
<b>MECHANICAL</b>			
Tensile Strength MD TD	lb/in <sup>2</sup>	ASTM D882	9,000 9,500
Elongation MD TD	%	ASTM D882	100 100
<b>PHYSICAL</b>			
Yield	in <sup>2</sup> /lb		14,600
COF Sealant side		ASTM D1894	<.40
<b>BARRIER</b>			
MVTR	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 100%RH	0.5
OTR	cc/100 in <sup>2</sup> /day	ASTM D3985 23°C, 0%RH	6
<b>THERMAL</b>			
Recommended Sealing Temperature	F	ASTM D1525	284° - 320°

#### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

#### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

**Disclaimer:** Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Platinum Packaging Group assumes no liability whatsoever in connection with the use of this information.