

FILM PRODUCT 2017 UPDATED	SEALING TO								GAUGE	FEATURES OF FILM
	PP	APET	RPET	CPET	ALU /FOIL	PS	PE	PVC		
SPX (AF) * **	NS	***	***	**	**	NS	NS	***	50, 100, 120	# Strong peel film for APET & APET lined CPET trays. Ideal for produce & general use Options of SPX LT& LT 30 / SPX 55
HSPET L ** * #	***	*	*	***	NS	NS	NS	*	92,118 , 164	# Lidding to CPET and PP
Plat GPE * **	***	**	***	***	***	***	***	***	50, 75, 100	# Seals all substrates. GPG / 6 GSM 100g 9 GSM
Plat GPE-AF *	**	**	**	**	**	**	**	**	50, 75, 100	# Seals all substrates. As above See GPE
Seal2Foil (AF) *	NS	NS	NS	NS	***	NS	NS	NS	208	\$ # Laminate sealing to foil trays. Sterilisable. Can be high barrier
Platpeel EVA HT (E) * **	***	**	***	***	***	***	***	***	208	Laminate sealing to all substrates. Good for misaligned sealing moulds. /Barrier available too
Plat Peel HT and HT (E) * **	***	NS	NS	NS	NS	NS	NS	NS	170,	\$ Retortable, boilable peelable laminate for PP & HDPE trays. Barrier available too
Plat Non-Peel and Non Peel CPP **	Weld	NS	NS	NS	NS	NS	NS	NS	180	Laminate Non-Peel to PP Cont.
HSPET 6 H **	NS	***	**	NS	NS	NS	NS	NS	75, 100	# APET, APET lined CPET trays. Peelable lidding
HSPET 6 * Pizza Film **	NS	**	*	NS	NS	NS	NS	NS	168	Light Peelable only for overwrap of pizza
Plat CAW 6 Pizza Film * **	NS	*	*	NS	NS	NS	NS	*	50, 100	# Peelable PET film for microwave cooking. Self venting
HSPET 9 (also HSPET25, 500)	NS	Weld	NS	NS	NS	NS	NS	NS	60, 80	#Ovenable overwrap.
PET 9 HPP	NS	WELD	NS	NS	NS	NS	NS	NS	120g 160	# High Pressure Pasteurization lidding for APET
Resealer	Weld	Weld	Weld	Weld	Weld	Weld	Weld	Weld	200	Different grades available to seal to PP, PS, APET & PE SEALANT BREAKS and remains on the flange and then can re-seal
PlatScribe	WELD Reseal									Custom Peelable laminate for All substrate

** Stocked Item * Microwaveable and freezable # Ovenable \$ Hot Sterilisable + ETO sterilisable

*** STRONG PEEL ** MEDIUM PEEL * EASY PEEL NS: NO SEAL