

PLATSEAL

RESEAL PET BARRIER AF GAF-5

Technical Data Sheet

KEY FEATURES

- Transparent, heat sealable PET/PE based laminate film with barrier, resealable and antifog properties.
- Ambient and chill tray lidding applications also suitable for form, fill, seal application.
- Sealing to APET, CPET and itself.
- Strong resealable closure.
- Low oxygen permability
- Excellent antifog properties.



Seals To										Suitable For				
CPET	MONO CPET	APET	pp	PE	PS	FOIL	LACQ FOIL	Pulp	Pressed Board	Coated Board	Gas Flush	Retort	Oven	Microwave
R	-	R	-	-	-	-		-	-	@	-	-	-	

P Peel W Weld Seal Only R Reseal Subject to Lacquer Type *

Property	Unit	Typical Values
Thickness	µm	75
Stable Temperature	°C	-40 to 200
Sealing Range	°C	150 to 180
Sealing Strength	N/15mm	> 3
Melting Point	°C	260 ¹
Yield	m ² /kg	12.2
WVTR	g/m ² /24hr@ 38° C, 90% RH	< 7
Gas Transfer Rate O ₂	cm ³ /m ² /24hr@ 23° C, 50% RH	< 2.5
Gas Transfer Rate CO ₂	cm ³ /m ² /24hr@ 23° C, 50% RH	< 12

Food Contact and Storage Information

Complies with EC Regulations 1935/2004 and 10/2011 Please note that it is the responsibility of the user to test the suitability of our product for the intended application in combination with the actual food stuff.

Product must be stored at ambient temperature (15-25° C recommended), 40-60% relative humidity, out of direct sunlight or heat sources. It should be allowed to reach operating room temperature before use

The above information is presented in good faith, however no warranty, express or implied, is given. Values listed are typical and are not to be constructed as a specification. All testing is in accordance to relevant ASTM standards.

**THE
PLATINUM
PACKAGING
GROUP**

7627 SOMERSET BLVD.
PARAMOUNT, CA 90723
TEL: (562) 630-6700
FAX: (562) 630-6716
WWW.PLATINUMPKGGROUP.COM

PLATSEAL
Vertical Rollstock
Overwrap & Lidding Films

**PLAT PEELABLE
LIDDING**
For All Tray Types
LAMINATED
& COATED